

## TECHNICAL DATA

### EVERLAY PROTECTION - thickness 4,7 mm

REV. 01 - 06/2019
-------------------

Rolls: height cm 200, lenght 20 m. Weight: 1,9 kg/m<sup>2</sup>

<u>PROPERTIES</u> <u>EN 13984</u>	<u>TEST</u> <u>METHODS</u>	<u>UNIT OF</u> <u>MEASURE</u>	<u>AVERAGE VALUES</u> <u>FROM</u> <u>MANUFACTURING</u> <u>CONTROLS</u>
Overall thickness	ISO 24346	mm	<b>4,7</b>
Mass per unit area	ISO 23997	g/m <sup>2</sup>	<b>1900</b>
Fire classification	EN 13501-1 (loose-laid)	class	<b>E</b>
Resistance factor to diffusion of water vapour (μ)	EN 1931 method B	-	<b>7897</b>
Water tightness	EN 1928	-	<b>waterproof</b>
<u>OPTIONAL</u> <u>PROPERTIES</u>	<u>TEST</u> <u>METHODS</u>	<u>UNIT OF</u> <u>MEASURE</u>	<u>AVERAGE VALUES</u> <u>FROM</u> <u>MANUFACTURING</u> <u>CONTROLS</u>
Shock absorption (glued with Mondoflex 2,5 mm)	EN 14808	%	<b>29</b>
Shock absorption (glued with Vinylsport 2 mm)	EN 14808	%	<b>30</b>
Thermal resistance	EN 12667	m <sup>2</sup> K/W	<b>0,09</b>
Thermal conductivity	EN 12667	W/mK	<b>0,05</b>
Dimensional stability	ISO 23999	%	<b>0,2</b>
Curling after exposure to heat	ISO 23999	mm	<b>2</b>
Volatile Organic Compounds (VOC) French Decret 2011-321	ISO 16000	class	<b>CLASS A+</b>

Mondo keeps the right to modify the characteristics of the products in any moment.