

TECHNICAL DATA

EVERLAY HIGH PROTECTION - thickness 7,5 mm

REV. 00 - 05/2017

Rolls: height cm 200, lenght 20 m. Weight: 2,6 kg/m²

<u>GENERAL REQUIREMENTS</u>	<u>TEST METHODS</u>	<u>UNIT OF MEASURE</u>	<u>AVERAGE VALUES FROM MANUFACTURING CONTROLS</u>
Overall thickness	ISO 24346	mm	7,5
Mass per unit area	ISO 23997	g/m ²	2600
Density	ISO 845	kg/m ³	350
Dimensional stability	ISO 23999	%	0,2
Curling after exposure to heat	ISO 23999	mm	2
<u>ESSENTIAL REQUIREMENTS</u>	<u>TEST METHODS</u>	<u>UNIT OF MEASURE</u>	<u>AVERAGE VALUES FROM MANUFACTURING CONTROLS</u>
Thermal resistance	EN 12667	m ² K/W	0,15
Thermal conductivity	EN 12667	W/mK	0,05
<u>OPTIONAL PROPERTIES</u>	<u>TEST METHODS</u>	<u>UNIT OF MEASURE</u>	<u>AVERAGE VALUES FROM MANUFACTURING CONTROLS</u>
Shock absorption (glued with Mondoflex 2,5 mm)	EN 14808	%	39

Mondo keeps the right to modify the characteristics of the products in any moment.