



PROVISIONAL TECHNICAL DATA issued in accordance with the EN 14904 standard

VINYLSPORT M EVERLAY 8,75 mm

REV. 00 - 04/2019

Weight: 5,75 kg/m²

<u>SAFETY IN USE PROPERTIES</u>	<u>TEST METHODS</u>	<u>UNIT OF MEASURE</u>	<u>REQUIREMENTS EN 14904</u>	<u>AVERAGE VALUES RESULTING FROM PRODUCTION CONTROLS</u>
Slip resistance	EN 13036-4 (dry)	-	80 ÷ 110	90
Shock absorption	EN 14808	%	25 ÷ 75	33 (type P1)
Vertical deformation	EN 14809	mm	≤ 5	1,3 (type P1)
<u>TECHNICAL PROPERTIES</u>	<u>TEST METHODS</u>	<u>UNIT OF MEASURE</u>	<u>REQUIREMENTS EN 14904</u>	<u>AVERAGE VALUES RESULTING FROM PRODUCTION CONTROLS</u>
Vertical ball behaviour	EN 12235	%	≥ 90	≥ 95
Resistance to a rolling load (1500 N)	EN 1569	mm	≤ 0,5	in conformity (no damage)
Resistance to wear	EN ISO 5470-1 (H18 wheels, 1 kg, 1000 cycles)	mg	≤ 1000	100
Fire classification	EN 13501-1	class	-	CLASS C _{fl} -s1 with o without adhesive
Specular gloss	EN ISO 2813	%	manifold	in conformity
Resistance to indentation	EN 1516	mm	≤ 0,5	in conformity
Resistance to impact	EN 1517	mm	≤ 0,5	in conformity (no damage)
<u>OPTIONAL PROPERTIES</u>	<u>TEST METHODS</u>	<u>UNIT OF MEASURE</u>	<u>REQUIREMENTS</u>	<u>AVERAGE VALUES RESULTING FROM PRODUCTION CONTROLS</u>
Dimensional stability	ISO 23999	%	-	0,05
Curling after exposure to heat	ISO 23999	mm	-	0,2

Mondo keeps the right to modify the characteristics of the products in any moment.