

TECHNICAL DATA

MONDOFLEX Thickness 2,5 mm

REV. 1 - 05/2020

Length: 18 m

Width: 190 cm

Weight: 3,75 kg/m²

TECHNICAL PROPERTIES	TEST METHODS	UNIT OF MEASURE	REQUIREMENTS	VALUES FROM MANUFACTURING CONTROLS
Total thickness	EN ISO 24346	mm	2,35 ± 2,65	2,5
Thickness of wear layer	EN ISO 24340	mm	0,85 ± 1,15	1,0
Mass per unit area	EN ISO 23997	g/m ²	-	3750
Rolls width	EN ISO 24341	cm	≥ nominal value	190
Rolls length	EN ISO 24341	m	≥ nominal value	18
Hardness	ISO 7619-1	Shore A	≥ 75	80
Residual indentation (after static loading)	EN ISO 24343-1	mm	≤ 0,20	0,1
Flexibility (method A)	EN ISO 24344 method A	-	no fissuring	no fissuring
Dimensional stability	EN ISO 23999	%	≤ 0,4	0,35
Abrasion resistance	ISO 4649 method A vertical load 5 N	mm ³	≤ 250	150
Colour fastness to artificial light	ISO 105 -B02 method 3	grade	blu scale ≥ 6 grey scale ≥ 3	in conformity
Effect of castor chair	EN 425	-	no surface change except dullness	suitable with wheels type W
Classification	EN ISO 10874	class	-	21-23/31-34/41-43
Fire classification	EN 13501-1	class	-	
Dynamic coefficient of friction	EN 13893	-	≥ 0,3	in conformity
Electrostatic Charge	EN 1815	kV	< 2 (antistatic)	in conformity
Electrical resistance (R1)	EN 1081	Ohm	-	≥ 10 ¹⁰
Thermal conductivity	EN 12667	W/mK	-	0,32
Thermal resistance	EN 12667	m ² K/W	-	0,008
OPTIONAL PROPERTIES	TEST METHODS	UNIT OF MEASURE	REQUIREMENTS	VALUES FROM MANUFACTURING CONTROLS
Improvement in footfall sound absorption	ISO 10140-3/717-2	dB	-	8
Stain resistance	EN ISO 26987	-	-	no surface change
Resistance to burning cigarette	EN 1399	class	method A ≥ 4 method B ≥ 3	method A ≥ 4 method B ≥ 3
Slip resistance	EN 13036-4	-	-	95
Shock absorption	EN 14808	%	-	4
Vertical deformation	EN 14809	mm	-	≤ 0,15
Vertical ball behaviour	EN 12235	%	-	≥ 98
Rolling load behaviour (1500 N)	EN 1569	mm	-	≤ 0,5 (no damage)
Resistance to wear	EN ISO 5470-1 (H18 wheels, 1 kg, 1000 cycles)	mg	-	900
Specular gloss	EN ISO 2813	%	-	≤ 30
Resistance to indentation	EN 1516	mm	-	0,025
Resistance to impact (mass 800 g; height 1 m)	EN 1517	mm	-	Absence of perceivable cracking, splitting, delamination; permanent indentation ≤ 0,5 mm
Volatile Organic Compounds (VOC) French Decret 2011-321	ISO 16000	class	manifold	CLASS A+