

## TECHNICAL DATA

### RAMFLEX INTERLOCK Thickness 8 mm

REV. 2 - 01/2020

TECHNICAL PROPERTIES	TEST METHODS	UNIT OF MEASURE	REQUIREMENTS	VALUES FROM MANUFACTURING CONTROLS
Total thickness	EN ISO 24346	mm	7,85 ÷ 8,15	8,0
Thickness of wear layer	EN ISO 24340	mm	2,05 ÷ 2,35	2,2
Mass per unit area	EN ISO 23997	g/m <sup>2</sup>	-	10800
Tiles dimension	EN ISO 24342	cm	nominal value ± 0,15 %	90x90
Hardness	ISO 7619-1	Shore A	≥ 75	in conformity
Residual indentation (after static loading)	EN ISO 24343-1	mm	≤ 0,20	0,175
Flexibility (method A)	EN ISO 24344 method A	-	no fissuring	no fissuring
Dimensional stability	EN ISO 23999	%	≤ 0,4	in conformity
Abrasion resistance	ISO 4649 method A vertical load 5 N	mm <sup>3</sup>	≤ 250	100
Colour fastness to artificial light	ISO 105 -B02 method 3	grade	blu scale ≥ 6 grey scale ≥ 3	in conformity
Effect of castor chair	EN 425	-	no surface change except dullness	suitable with wheels type W
Classification	EN ISO 10874	class	-	21-23/31-34/41-43
Fire classification	EN 13501-1	class	-	CLASS C <sub>fl</sub> - s2 with or without adhesive
Dynamic coefficient of friction	EN 13893	-	≥ 0,3	in conformity
Electrostatic Charge	EN 1815	kV	< 2 (antistatic)	in conformity
Electrical resistance (R1)	EN 1081	Ohm	-	10 <sup>10</sup>
Thermal conductivity	EN 12667	W/mK	-	0,3
Thermal resistance	EN 12667	m <sup>2</sup> K/W	-	0,027
OPTIONAL PROPERTIES	TEST METHODS	UNIT OF MEASURE	REQUIREMENTS	VALUES FROM MANUFACTURING CONTROLS
Improvement in footfall sound absorption	ISO 10140-3/717-2	dB	-	15,5
Stain resistance	EN ISO 26987	-	-	no surface change (*)
Slip resistance	EN 13036-4	-	-	85
Shock absorption	EN 14808	%	-	10
Vertical deformation	EN 14809	mm	-	≤ 0,6
Vertical ball behaviour	EN 12235	%	-	≥ 98
Rolling load behaviour (1500 N)	EN 1569	mm	-	≤ 0,5 (no damage)
Resistance to wear	EN ISO 5470-1 (H18 wheels, 1 kg, 1000 cycles)	mg	-	500
Specular gloss	EN ISO 2813	%	-	≤ 30
Resistance to indentation	EN 1516	mm	-	0,075
Resistance to impact	EN 1517	mm	-	≤ 0,5 (no damage)
Volatile Organic Compounds (VOC) French Decret 2011-321	ISO 16000	class	manifold	CLASS A+

(\*) when tested by means of detergents specifically used for rubber